

3/2/00 op #'s DH 498, TF 751, BK 720

Test: Covered CS electrodes for
chronic ^{19 REX} animal study - Goa Lot #000630/

- wrapped 20 times with F4 roll 8A Batch # SK F4004 (17 electrodes)
- used a mandril ~ 18" to slide electrode on
- using Gore-tex CV 7 suture, slide suture between filars to mask .180" from end of coil per spec drawing on page 51 (2" electrode of CPTs)
- after wrapping remove suture by pulling on one end
- sintered @ 370°C in large clean room using wipe down lumen of electrode and hang on shelf rack, oven # 7399 for 10'
- PVA'd on 3/3/00 per page 51 of this lab book
15' IPA, 70' PVA, 20' DI RINSE, 120' Glutar / HCL, 60' DI Rinse
²⁷⁰ (10,10) ⁵⁰ 290 190 (20,20,80)
sterile H₂O used for HA DI H₂O used

Enter lot # 2428A54
HCL lot # 2062KVHA
PVA lot # MC0131

- 1 500 ml batch of PVA made on 2/9/00 used three times in clean room
1 500 ml batch of PVA made fresh for page 51 (made on 2/25/00) used once for page 51 in clean room

3 covered coils were retained. 1 coil was dirty prior to PVA treatment, 2 coils PSE not PVA treated and 2 coils were PVA treated.

- retain attached LEAD # 7109104572 sent back from after manufacturing

Robert C. Kall

Deborah Hernandez

3/2/00

3-2-00

BEST AVAILABLE COPY